

# Lastofalt® Flooring [Technical Specifications]

**Technical specifications**

floor thickness	: 12 - 20 mm
max. compression strength	: 60 N/mm <sup>2</sup>
bow and tensile strength	: 12 - 15 N/mm <sup>2</sup>
adhesion	: 2 - 3 N/mm <sup>2</sup> [crack in concrete]
elasticity modules	: 10700 N/mm <sup>2</sup>
heat-conducting	: 1,163 W/mK
shrinkage	: 0,3 mm/m
surface resistance	: 6.10 Ohm
punchsolidity	: 20 kV/cm

**Cold resistance** No changes of characteristics after frost/thaw cycles +15/-15°C.

**Chemical resistance** Resistant against oils, fats, salts, sugars, alcohol and solvents.

The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.



Hoogewaard 183 Postbus 6 2396 ZG Koudekerk aan den Rijn

Tel.071-341 91 08 Fax.071-341 59 46

E-mail:info@latexfalt.com www.latexfalt.com