

Spectrasfalt® JE Primer

| | | |
|--------------------|--|---|
| Composition | Spectrasfalt JE Primer is a bonding agent, made from a polymer, dissolved in an organic solvent, combined with adhesion - reinforcing materials. | |
| Properties | density | : approx. 1.000 kg/m ³ |
| | drying time [in open air at 15°C] | : approx. 30 min. |
| | inflammability | : slightly inflammable [contains heptane] |
| Uses | As a bonding agent between a Latexfalt rubber-bitumen product [as Spectrasfalt JE, Spectrasfalt RJ, Spectrasfalt ES] and the subsurface [concrete, stone, natural stone, asphalt]. | |
| Application | Spectrasfalt JE Primer should be stirred well before use. Clean and dry the surface that has to be treated. No dust, dirt, grease, old coatings or loose particles may remain. Spectrasfalt JE Primer must be cold applied with a brush, broom or roller. Depending on the roughness of the subsurface, coverage is approx. 0,15 kg/m ² . | |
| Warning | Spectrasfalt JE Primer is slightly inflammable and contains heptane. Application only in well-ventilated areas; avoid breathing fumes and spray mist. Smoking, naked flames and use of motors which are not explosion-protected is not allowed. Take steps to avoid discharge of static electricity. Do not dispose of waste down the sink. | |
| Packaging | In tins of 5 litres and 25 litres. | |
| Storage | Spectrasfalt JE Primer can be stored indefinitely in the sealed packaging. Store in an area that is in conformity with the hazard category. | |

The information submitted in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

23-02-2006



Hoogewaard 183 Postbus 6 2396 ZG Koudekerk aan den Rijn

Tel.071-341 91 08 Fax.071-341 59 46

E-mail:info@latexfalt.com www.latexfalt.com